

Material and Application Guide

3 X 1 Blast Furnace Slag – Levy Plant #1



EDW. C. LEVY CO.

8800 Dix Avenue, Detroit, Michigan 48209

Phone (313) 429-LEVY

Fax (313) 429-2448

e-mail sales@edwclevy.net

<http://www.edwclevy.com>

- Material:** Blast Furnace Slag
- Product:** 3 X 1 – Commercial (Levy)
- Location:** Levy Plant #1
- Applications:** Structural fill
Stabilizing fill
Light weight embankments
Rail ballast material

Description: An open graded coarse aggregate, produced by crushing and screening air-cooled iron Blast Furnace Slag. A light brown to gray crystalline aggregate formed simultaneously with the production of iron in a blast furnace. The particles are sized from 3" (75.0mm) to ¾" (19.0mm).



3 X 1 Blast Furnace Slag – NOT ACTUAL SIZE (80% of full size)

Specifications: Commercial (Levy)

3 X 1 Blast Furnace Slag conforms to all the requirements of the Edw. C. Levy Co. specifications for 3 X 1 Blast Furnace Slag

Gradation:

U.S. Sieve	4"	3"	2½"	2"	1½"	1"	¾"
Metric Sieve	100.0mm	75.0mm	65.5mm	50.0mm	37.5mm	25.0mm	19.0mm
Specification	100	95-100	90-100	80-90	65-80	25-55	0-15

Physical Properties:

- ASTM C 29, Loose Unit Weight – 67 lb/ft³
- ASTM C 29, Jigged Unit Weight – 78 lb/ft³

*These weights are representative of the material in our yard and do not reflect the effects of handling, transportation, and placement.

General Usage Guide:

When used as a structural or stabilizing fill, the 3 X 1 Blast Furnace Slag should be placed on the prepared ground in lifts not exceeding 8". The total thickness of the 3 X 1 Blast Furnace Slag needed will depend on the ground conditions and the design loadings. Consult the design plans or engineer's recommendations. 3 X 1 Blast Furnace Slag can be used to provide support in areas of poor subgrade.